



Artículo/Article	MICROFIBRA 86 TECNOSANI		(test itel CE-11343)				
REUSABLE (>25 washes)	MADE IN SPAIN		TESTED (ACCORDING UNE-EN14683 and UNE-0065 CEE/93/42)				
ANÁLISIS FÍSICO / PHYSICAL ANALYSIS							
CARACTERÍSTICAS		RESULTADOS / RESULTS		VALORES / VALUES	TEST		
Nº de Hilo/Thread Count	Urdimbre / Warp		75D				
	Trama / Weft		150D				
Densidad / Density	Urdimbre / Warp		104				
	Trama / Weft		71				
Ligamento / Weave	PLANA / PLAIN						
Comp. Urd./ Comp. Warp	100% PES				ISO 1833:2006		
Comp. Tr./ Comp.Weft	100% PES						
Total Comp.	100% PES				Simple: No tolerancia Compuesta: +/- 3%		
Ancho Final / Final Width	cm	160 - 165		+/- 2%	ISO 3932:1976		
Peso / Weight	gr/m ²	82 - 86		+/- 5%	ISO 3801:1977		
Resistencia Rotura/ Breakage	(Kgs.)	Urdimbre	pass		kgf	EN-13795	
		Trama	pass		kgf		
Resistencia Abrasion	pass				EN-13795		
Resistencia Desgarro / Tear	Urdimbre/Warp (G)	N/A		Trama / Weft	N/A	EN-13795	
Encogimiento / Shrinkage	° C	60	% Urdimbre	+/- 2		0 - 3 %	NP EN ISO 5077:2008
			% Trama	+/- 2			
SPECIAL MEDICAL TESTS							
CARACTERÍSTICAS		RESULTADOS / RESULTS		VALORES / VALUES	TEST		
Washing solidity 60°C	4,5		0-5		UNE EN ISO-05		
Pilling	5		0-5		UNE EN ISO 12945-2		
Traspirability	< 60 Pa/cm ²				AST1		
Aerosol Filtration Efficiency	>95%				UNE EN14683		
Particle Filtration Efficiency	>94%				UNE EN14683		
Particle Filtration	0,3 micras and >95% efficiency				UNE EN149		
Bacterian presence	DRY: PASS		WET: PASS		EN-13795		
ANÁLISIS QUÍMICO / CHEMICAL ANALYSIS							
CARACTERÍSTICAS		RESULTADOS / RESULTS		VALORES / VALUES	TEST		
pH	Conforme/According Oeko-Tex II		4,0 - 7,5		UNI EN ISO 3071/06		
Formaldehído	Conforme/According Oeko-Tex II		<16ppm	<75ppm	UNE EN ISO 14184-1:1999		
Arlaminas	Conforme/According Oeko-Tex II		20 ppm		UNE 2002/61/CE		
PROHIBIDOS / FORBIDDEN							
Metales Pesados	Conforme/According Oeko-Tex II		Niquel 0,5 Pg/cm ² - Cadmio 75 pm - Plomo 100 ppm				
AZO Colorants	Conforme/According Oeko-Tex II		No detectable				
Colorantes Alérgicos	Conforme/According Oeko-Tex II		No detectable (LMBG) (1/4/96)				
SÍMBOLOS DE LAVADO/ WASH CARE SYMBOLS							
Observaciones:							
TRAS 25 LAVADOS EL ACABADO EMPIEZA A PERDER PROPIEDADES - LAVAR CON DETERGENTE NEUTRO							
AFTER 25 WASHES THE FINISH BEGINS TO LOSE PROPERTIES - WASH WITH NEUTRAL DETERGENT							
NO USAR LEJIA / DO NOT USE BLEACHING							
PLANCHADO A 140° de 10-15 SEGUNDOS / IRON 140° FOR 10-15 SECONDS							
GRS POST CONSUME bajo pedido / on request							